

# Klüberpaste UH1 96-402

Light-coloured high-temperature paste for the food-processing and pharmaceutical industries



## Your benefits at a glance

- Reliable dry lubrication at temperatures from 200 °C to 1200 °C
- Good adhesion to the friction point, also when subject to humidity
- ISO 21469 certified – supports the compliance with the hygienic requirements in your production. You will find further information about ISO Standard 21469 on our website [www.klueber.com](http://www.klueber.com)

## Your requirements - our solution

Klüberpaste UH1 96-402 is a high-temperature paste designed for versatile assembly purposes in hygienically sensitive environments. It contains fully synthetic base oils and a special blend of ceramic solid lubricants.

Across the “normal” temperature range up to approx. 160 °C, Klüberpaste UH1 96-402 is a water-resistant lubricating and assembly paste providing good adhesion on metals.

Under permanently higher temperatures up to 1200 °C, its solid lubricating particles provide protection against tribocorrosion or fretting corrosion.

Klüberpaste UH1 96-402 is NSF H1 registered and therefore complies with FDA 21 CFR § 178.3570. The lubricant was developed for incidental contact with products and packaging materials in the food-processing, cosmetics, pharmaceutical or animal feed industries. The use of Klüberpaste UH1 96-402 can contribute to increase reliability of your production processes. We nevertheless recommend conducting an additional risk analysis, e.g. HACCP.

## Application

Klüberpaste UH1 96-402 is suitable for a variety of friction points in food-processing and pharmaceutical machines which are subject to high loads

- as an assembly paste for transition and loose fits to prevent fretting corrosion
- as a paste for screw connections based on high-alloy steels to optimise the tightening torque and demounting, even after

long operating periods

- as a long-term lubricant for low-speed guide rails, hinges, rollers, etc.

## Application notes

Before applying KlüberpasteUH1 96-402 it is important to clean and degrease the contact surfaces thoroughly. A thin layer of the paste is then applied by brush, leather cloth or synthetic sponge.

Klüberpaste UH1 96-402 spreads easily over the entire surface, facilitating easy processing. We recommend carrying out compatibility tests before applying the paste to plastic materials.

Equipment manufacturers and operators should therefore conduct risk analyses prior to such applications. Measures to exclude health or injury risks are to be undertaken if necessary.

Opened packs must be thoroughly closed again after use to protect the paste from contamination.

The friction values indicated on page 2 in the Section Product Data were determined with two different materials. Other materials/surfaces have to be checked accordingly.

For more details on MOSH/MOAH and their assessment in H1 lubricants, please visit our website or contact your Klüber representative.

## Material safety data sheets

Material safety data sheets can be requested via our website [www.klueber.com](http://www.klueber.com). You may also obtain them through your contact person at Klüber Lubrication.

### Pack sizes

Cartridge 600 g

### Klüberpaste UH1 96-402

+

# Klüberpaste UH1 96-402

Light-coloured high-temperature paste for the food-processing and pharmaceutical industries



Pack sizes	Klüberpaste UH1 96-402
Can 750 g	+
Bucket 30 kg	+

  

Characteristics	Klüberpaste UH1 96-402
Article number	005116
Colour	light grey
Service temperature, lower limit	-30 °C
Service temperature, upper limit	1200 °C
NSF H1 registration number	056338
NLGI grade, DIN 51818	2
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	approx. 57 mm <sup>2</sup> /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	approx. 360 mm <sup>2</sup> /s
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 164 h	≤ 1 corrosion degree
Four-ball tester, welding load, DIN 51350-4	≥ 2600 N
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, averaged bearing surface friction coefficient (initial tightening), external test	0.13
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, averaged thread friction coefficient (initial tightening), external test	0.11
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, standard deviation (S) of averaged bearing surface friction coefficient (initial tightening), external test	0.018
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, standard deviation (S) of averaged thread friction coefficient (initial tightening), external test	0.009
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, averaged bearing surface friction coefficient (initial tightening), external test	0.12
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, averaged thread friction coefficient (initial tightening), external test	0.11

# Klüberpaste UH1 96-402

Light-coloured high-temperature paste for the food-processing and pharmaceutical industries



Characteristics	Klüberpaste UH1 96-402
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, standard deviation (S) of averaged bearing surface friction coefficient (initial tightening), external test	0.01
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$ , number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, standard deviation (S) of averaged thread friction coefficient (initial tightening), external test	0.019
Water resistance, DIN 51807-1, 3 h, 90°C	≤ 1 - 90 rating
Mineral Oils associated with, MOAH (Mineral Oil Aromatic Hydrocarbons), (Information based on recipe. The presence of impurities, cannot be ruled out.)	No component of recipe
Mineral Oils associated with, MOSH (Mineral Oil Saturated Hydrocarbons), (Information based on recipe. The presence of impurities, cannot be ruled out.)	No component of recipe
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	24 months

## Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 95 years.

Klüber Lubrication München GmbH & Co. KG /  
Geisenhausenerstraße 7 / 81379 München / Germany /  
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.