

Klüberplex BEM 41-132

High-temperature and long-term grease for rolling bearings



Your benefits at a glance

- Longer service life due to special wear additives for roller bearings
- Less maintenance
- Versatile grease due to wide operating temperature range and optimised oil release

Your requirements - our solution

Klüberplex BEM 41-132 is based on synthetic hydrocarbon oil, mineral oil and a special lithium soap. Special additives ensure optimum oxidation resistance as well as protection against wear and corrosion.

Application

Klüberplex BEM 41-132 can be used for long-term or lifetime lubrication of rolling bearings.

For rolling bearings with a high degree of sliding friction, e.g.

- tapered roller bearings
- cylinder roller bearings
- spherical roller bearings

or

for-life lubricated deep groove ball bearings

and

rolling bearings e.g. in

- paper-making machines (dry section)
- textile machines (dry section)
- electric motors
- hot air blowers
- drying ovens
- air separators in the base materials industry

- generators in wind power plants

or

rolling bearings in vehicle components

- clutch bearings
- generator bearings
- water pump bearings
- fluid fan bearings

Application notes

Klüberplex BEM 41-132 is applied by means of spatula, brush or grease gun. For application via automatic lubricating systems, pumpability should be checked beforehand. Prior to series application we recommend testing the compatibility of the lubricant with the materials in contact.

This product is also available in our automatic lubricant dispenser Klübermatic. Please consult the application engineering experts from Klüber Lubrication to determine whether Klübermatic might be used under the conditions in your processes.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüberplex BEM 41-132
Cartridge Lube-Shuttle 370 g	+
Cartridge 400 g	+
Can 1 kg	+
Bellow 5 kg	+
Bucket 25 kg	+

Klüberplex BEM 41-132

High-temperature and long-term grease for rolling bearings



Pack sizes	Klüberplex BEM 41-132
Bucket 50 kg	+
Drum 170 kg	+
Characteristics	Klüberplex BEM 41-132
Article number	020256
Composition, thickener	lithium complex soap
Composition, type of oil	mineral oil , synthetic hydrocarbon oil
Colour space	yellow
Service temperature, lower limit	-40 °C
Service temperature, upper limit	150 °C
Lubricating greases - K, DIN 51825@DIN 51502	KPHC2N-30L
Density, Klüber method: PN 024, 20°C	approx. 0.9 g/cm ³
NLGI grade, DIN 51818	2
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	265 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	295 0.1 mm
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , lower limit	3000 mPas
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , upper limit	6000 mPas
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	approx. 14 mm ² /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	approx. 120 mm ² /s
Copper corrosion, DIN 51811, 24 h, 120°C	1 - 120 - 24 corrosion degree
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 164 h	≤ 1 corrosion degree
Oil separation, ASTM D6184, based on standard, 30 h, 150°C	≤ 8 % by weight
Oil separation, DIN ISO 22285, 168 h, 40°C	≤ 4 % by weight
Low temperature torque, IP 186, -40°C, running torque	≤ 200 mNm
Low temperature torque, IP 186, -40°C, starting torque	≤ 1000 mNm
Dropping point, DIN ISO 22286 / IP 396	≥ 250 °C
FAG FE9 rolling bearing test, DIN 51821-2, 1500 / 6000-150, service life F50	≥ 100 h
Shell roll stability, ASTM D1831, based on standard, 50 h, 100°C, penetration difference	≤ +80 0.1 mm
Speed factor (n x dm)	approx. 1000000 mm/min
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüberplex BEM 41-132

High-temperature and long-term grease for rolling bearings



Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 95 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.